

ROAD-CEL®

natural cellulose fibers

Grade
RC

Basic material

Highly purified cellulose

Characteristic

Coarse fiber, grey

CAS No. 9004-34-6

Physical and chemical properties

Cellulose content, %

Fiber length, average 6 mm Max

Fiber diameter, average 40 micron

Bulk density, loose, g/L

Brightness, %

Ash, % 18.0 ± 5.0%

pH – value 7.5 ± 1.0

Typical screen analysis

(according to industry standard DIN 53734/air jet sieve)

<u>Mesh aperture:</u>	<u>300 microns</u>	<u>100 microns</u>	<u>32 microns</u>
Retained:		70.0 ± 10.0%	

General remarks

ROAD-CEL® cellulose fibers are environmentally friendly products made from natural raw materials. Typically they are used as thickeners, reinforcement fibers, absorbents, extenders, carriers or fillers in a variety of applications.

The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be Obtained from the use thereof, or that any such use will not infringe upon any patent. We cannot anticipate all conditions under which this information and/or products of other manufacturers in combination with our products, may be used We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product for their own use. Buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in conjunction with other products.

LIGNOCEL®, LIGNOFLOK®, ARBOCEL®, VITACEL®, REHOPLUS®, RAUCHERGOLD®, VIATOP®, VIVAPUR®, VIVASTAR®, and REHOFIX® are registered trademarks of J. Rettenmaier & Söhne GmbH + Co.



J. Rettenmaier USA LP
Fibers Designed by Nature
16369 US 131 Highway
Schoolcraft, MI 49087

Toll Free: (877) 895 4099
Telephone: (269) 679 2340
Telefax: (269) 679 2364